

APR 07 2009

Serial No. 10/736.117
Attorney Docket No. 7343-1
Reply to Office Action**Listing of Claims:**

1. (Previously Presented) A woven, patterned glass fiber textile fabric comprised of a glass fiber yarn with a titer of from about 30 to 75 tex as the warp, and a glass fiber yarn having a titer ranging from 190 to 350 tex as the weft, wherein the warp density of the fabric ranges from 2.5 to 5 threads/cm and the weft density ranges from 2.0 to 12 threads/cm, wherein the woven, patterned glass fiber textile fabric is formed from a Jacquard weaving process using a Jacquard loom, wherein each glass fiber yarn used as the warp and/or weft is a sliver or a texturized yarn.

2. (Canceled)

3. (Original) The glass textile fabric of claim 1, wherein the titer of the warp yarn is about 34 tex.

4. (Original) The glass textile fabric of claim 1, wherein the titer of the warp yarn is about 70 tex.

5. (Canceled)

6. (Original) The glass textile fabric of claim 1, wherein the titer of the weft yarn is about 200 tex.

7. (Original) The glass textile fabric of claim 1, wherein the titer of the weft yarn is about 330 tex.

8-10. (Canceled)

Serial No. 10/736,117
Attorney Docket No. 7343-1
Reply to Office Action

11. (Original) The glass textile fabric of claim 1, wherein the textile is impregnated with a chemical formulation comprised of a starch binder and a polymeric binder.

12. (Withdrawn) A method of making the woven, patterned glass fiber textile of claim 1, comprising the following steps: providing a patterned control Jacquard loom, and weaving a textile using the glass fiber warp yarn and the glass fiber weft yarn of claim 1.

13. (Withdrawn) The method of claim 12, wherein the titer of the glass fiber warp yarn ranges from 30 to 75 tex.

14. (Withdrawn) The method of claim 12, wherein the titer of the glass fiber warp yarn is about 34 tex.

15. (Withdrawn) The method of claim 12, wherein the titer of the glass fiber warp yarn is about 70 tex.

16-18. (Canceled)

19. (Withdrawn) The method of claim 12, wherein the textile is further impregnated with a chemical formulation comprised of a starch binder and a polymeric binder.

20. (Canceled)

21. (Withdrawn) The method of claim 12, wherein each glass fiber yarn used as the warp and/or weft is a sliver or a texturized yarn.